


Silente F.R. / Ref. SE/775

CHARACTERISTICS

Width cm	300
Thickness	0,33
Weight g/m2	126
Solar_Trasmission	55
Solar_Reflection	33
Solar_Absorption	12
Light_Transmission	53
Light_Absorption	38
GtotInt	0,48
UV_Reduction	65
Sound_Absorption	0,55
Ref.	SE/775
Composition	100% PL Trevira CS
F.R. Classification	Classe 1 (I), B1 (D)
HealthCertification	OEKO-TEX
Transparency	Transparent
Colour_fastness_to_light	4
Outdoor	No
Sealable	No
adjustable	No
jointed	No
IMO	No
Tone	Grey/Black




Rullo

Silente F.R. / Ref. SE/774

CHARACTERISTICS

Width cm	300
Thickness	0,33
Weight g/m2	126
Solar_Trasmision	56
Solar_Reflection	36
Solar_Absorption	8
Light_Transmission	54
Light_Absorption	39
GtotInt	0,48
UV_Reduction	65
Sound_Absorption	0,55
Ref.	SE/774
Composition	100% PL Trevira CS
F.R. Classification	Classe 1 (I), B1 (D)
HealthCertification	OEKO-TEX
Transparency	Transparent
Colour_fastness_to_light	4
Outdoor	No
Sealable	No
adjustable	No
jointed	No
IMO	No
Tone	Grey/Black




Rullo

Silente F.R. / Ref. SE/773

CHARACTERISTICS

Width cm	300
Thickness	0,33
Weight g/m2	126
Solar_Trasmision	57
Solar_Reflection	37
Solar_Absorption	6
Light_Transmission	55
Light_Absorption	40
GtotInt	0,5
UV_Reduction	65
Sound_Absorption	0,55
Ref.	SE/773
Composition	100% PL Trevira CS
F.R. Classification	Classe 1 (I), B1 (D)
HealthCertification	OEKO-TEX
Transparency	Transparent
Colour_fastness_to_light	4
Outdoor	No
Sealable	No
adjustable	No
jointed	No
IMO	No
Tone	Beige




Rullo

Silente F.R. / Ref. SE/772

CHARACTERISTICS

Width cm	300
Thickness	0,33
Weight g/m2	126
Solar_Trasmission	58
Solar_Reflection	39
Solar_Absorption	3
Light_Transmission	56
Light_Absorption	42
GtotInt	0,5
UV_Reduction	65
Sound_Absorption	0,55
Ref.	SE/772
Composition	100% PL Trevira CS
F.R. Classification	Classe 1 (I), B1 (D)
HealthCertification	OEKO-TEX
Transparency	Transparent
Colour_fastness_to_light	4
Outdoor	No
Sealable	No
adjustable	No
jointed	No
IMO	No
Tone	Natural




Rullo



Silente F.R. / Ref. SE/771

CHARACTERISTICS

Width cm	300
Thickness	0,33
Weight g/m2	126
Solar_Trasmision	59
Solar_Reflection	39
Solar_Absorption	2
Light_Transmission	57
Light_Absorption	42
GtotInt	0,52
UV_Reduction	65
Sound_Absorption	0,55
Ref.	SE/771
Composition	100% PL Trevira CS
F.R. Classification	Classe 1 (I), B1 (D)
HealthCertification	OEKO-TEX
Transparency	Transparent
Colour_fastness_to_light	4
Outdoor	No
Sealable	No
adjustable	No
jointed	No
IMO	No
Tone	Natural



Rullo